

Penguard Midcoat M20

Product description

Penguard Midcoat M20 is a high-solids, high-build, fast-curing midcoat designed for atmospheric areas. It is a two-component polyamine-cured epoxy coating pigmented with Micaceous Iron Oxide (MIO).

Typical use

Suitable for structural steel exposed to corrosive environments in atmospheric conditions.

Approvals and certificates

Tested in accordance to ISO 12944, up to C5 High, as a midcoat in selected system. Consult your Jotun representative for details.

Additional certificates and approvals may be available on request.

Colors

white, buff, light grey, medium grey, grey, grey XO, dark grey, off-white, red

Product data

Property	Test/Standard	Description	
Solids by volume	ISO 3233	80 ± 2 %	
Gloss level (GU 60 °)	ISO 2813	matt (0-35)	
Flash point	ISO 3679 Method 1	77 °F (25 °C)	
Density	calculated	1.6 kg/l	
Region	Regulation	Test Standard	VOC Value

The provided data is typical for factory produced products, subject to slight variation depending on color.

Gloss description: According to Jotun Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	4 mils (100 µm)	12 mils (300 µm)
Wet film thickness	5 mils (125 µm)	15 mils (375 µm)
Theoretical spreading rate	330 ft ² /gal (8 m ² /l)	110 ft ² /gal (2.7 m ² /l)

For DFT below 100 µm more thinner should be added.

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

Optimum performance, including adhesion, corrosion protection, heat resistance and chemical resistance is achieved with recommended surface preparation.

Application

Application methods

The product can be applied by

- Spray: Use airless spray.
- Brush: Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

Product mixing ratio (by volume)

Penguard Midcoat M20 Comp A	4 part(s)
Penguard Midcoat M20 Comp B	1 part(s)

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 17
Thinning max: 10 %

When applied with mist coat technique an even higher amount of thinner may be required.

Note: Korean VOC regulation "Korea Clean Air Conservation Act" and its corresponding thinning limit will prevail over recommended thinning volumes.

Guiding data for airless spray

Nozzle tip (inch/1000): 17-27
Pressure at nozzle (minimum): 150 bar/2100 psi

Drying and Curing time

Substrate temperature	-41 °F	32 °F	41 °F	50 °F	73 °F	104 °F
Surface (touch) dry	18 h	12 h	4 h	2 h	1.5 h	30 min
Walk-on-dry	42 h	26 h	12 h	7 h	4 h	2 h
Dried to over coat, minimum	40 h	24 h	10 h	6 h	3 h	1 h
Dried/cured for service		21 d	13 d	8 d	4 d	3 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature	73 °F
Pot life	1 h

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	140 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: zinc epoxy, zinc silicate, epoxy
Subsequent coat: epoxy, polyurethane, polysiloxane

Packaging (typical)

	Volume (liters)	Size of containers (liters)
Penguard Midcoat M20 Comp A	4 / 16	5 / 20
Penguard Midcoat M20 Comp B	1 / 4	1 / 5

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C)

Penguard Midcoat M20 Comp A 24 month(s)
Penguard Midcoat M20 Comp B 24 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Environmental Documentation

This product can contribute to Green Building Standard credits. Please refer to Jotun.com for more information or contact your local Jotun representative.

Environmental Product Declaration (EPD) is available at www.epd-norge.no

Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Color variation

When applicable, products primarily meant for use as primers or antifouling may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.